

Noryl* Resin LTA5020

Americas: COMMERCIAL

Noryl* LTA5020 is an unfilled, injection moldable grade. Designed for improved long term heat aging, this resin also uses non-chlorinated, non-brominated FR additives to achieve a V0 UL94 rating. Noryl LTA5020 is only available in a dark grey/black and may be an excellent material candidate for application requiring electrically insulating properties.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, yld, Type I, 50 mm/min	80	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.8	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	18	%	ASTM D 638
Tensile Modulus, 5 mm/min	2850	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	118	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2770	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	83	MPa	ISO 527
Tensile Stress, break, 50 mm/min	80	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	6	%	ISO 527
Tensile Modulus, 1 mm/min	2840	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	131	MPa	ISO 178
Flexural Modulus, 2 mm/min	2910	MPa	ISO 178
IMPACT	Value	Unit	Standard
Izod Impact, unnotched, 23°C	1400	J/m	ASTM D 4812
Izod Impact, notched, 23°C	90	J/m	ASTM D 256
Izod Impact, notched, -30°C	38	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	17	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	34	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	3	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	3	kJ/m ²	ISO 179/1eA
THERMAL	Value	Unit	Standard
Vicat Softening Temp, Rate B/50	137	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	128	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	112	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	134	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	116	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.9E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.9E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	135	°C	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	135	°C	ISO 306

Vicat Softening Temp, Rate B/120	137	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	115	°C	ISO 75/Af
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
PHYSICAL	Value	Unit	Standard
Specific Gravity	1.15	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 280°C/5.0 kgf	10	g/10 min	ASTM D 1238
Density	1.15	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.2	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	10	cm ³ /10 min	ISO 1133
ELECTRICAL	Value	Unit	Standard
Volume Resistivity	3.7E+16	Ohm-cm	ASTM D 257
Surface Resistivity	4.2E+14	Ohm	ASTM D 257
Dielectric Strength, in oil, 1.6 mm	30	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	18.6	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	2.87	-	ASTM D 150
Relative Permittivity, 1 MHz	2.76	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.025	-	ASTM D 150
Dissipation Factor, 1 MHz	0.003	-	ASTM D 150
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Comparative Tracking Index	275	V	IEC 60112
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Compliant, 94V-0 Flame Class Rating (3)(4)	1.5	mm	UL 94 by GE
UL Compliant, 94-5VA Rating (3)(4)	3	mm	UL 94 by GE
Glow Wire Flammability Index 960°C, passes at	1.5	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.5 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
UV-light, water exposure/immersion	f1	-	UL 746C

Source GMD, last updated:11/03/2008

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	105 - 110	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	275 - 305	°C
Nozzle Temperature	275 - 305	°C
Front - Zone 3 Temperature	265 - 305	°C
Middle - Zone 2 Temperature	255 - 300	°C
Rear - Zone 1 Temperature	245 - 295	°C
Mold Temperature	70 - 100	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 70	%
Vent Depth	0.038 - 0.051	mm

Source GMD, last updated:11/03/2008

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

- (1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Noryl is a trademark of the SABIC Innovative Plastics Company

© 1997-2009 SABIC Innovative Plastics Company. All rights reserved