

Noryl* Resin GFN2

Americas: COMMERCIAL

PPE+PS blend. 20% Glass reinforced. UL746C F1. NSF 61 listing in several colors (restrictions apply). FDA compliance (restrictions apply). Low water absorption. Hydrolytic stability. Dimensional stability. Suitable for fluid engineering applications including pump housings and impellers, valve components and others.

Property

TYPICAL PROPERTIES ⁽¹⁾			
	Value	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	90	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	6200	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	160	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	5800	MPa	ASTM D 790
Hardness, Rockwell L	106	-	ASTM D 785
Tensile Stress, break, 5 mm/min	97	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	7070	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	167	MPa	ISO 178
Flexural Modulus, 2 mm/min	6540	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	650	J/m	ASTM D 4812
Izod Impact, notched, 23°C	119	J/m	ASTM D 256
Izod Impact, notched, -40°C	96	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	22	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	11	kJ/m ²	ISO 179/2C
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	140	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	143	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.89E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.26E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	143	°C	ISO 306
Vicat Softening Temp, Rate B/120	146	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	143	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	137	°C	ISO 75/Ae
Relative Temp Index, Elec	90	°C	UL 746B
Relative Temp Index, Mech w/impact	90	°C	UL 746B
Relative Temp Index, Mech w/o impact	90	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Water Absorption, 24 hours	0.06	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.2 - 0.5	%	SABIC Method
Melt Flow Rate, 300°C/5.0 kgf	9	g/10 min	ASTM D 1238

Melt Volume Rate, MVR at 300°C/5.0 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL	Value	Unit	Standard
Dielectric Strength, in oil, 3.2 mm	16.5	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	2.86	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0008	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	4	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	4	PLC Code	UL 746A
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Recognized, 94HB Flame Class Rating (3)	1.47	mm	UL 94
Oxygen Index (LOI)	26	%	ASTM D 2863
UV-light, water exposure/immersion	F1	-	UL 746C

Source GMD, last updated:05/11/2004

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	110 - 120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	300 - 325	°C
Nozzle Temperature	300 - 325	°C
Front - Zone 3 Temperature	290 - 325	°C
Middle - Zone 2 Temperature	275 - 320	°C
Rear - Zone 1 Temperature	265 - 315	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 70	%

Source GMD, last updated:05/11/2004

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its

own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Noryl is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company.All rights reserved