

Noryl* Resin V02570

Americas: COMMERCIAL

Noryl* V02570 is a 25% milled fiber reinforced, injection moldable grade. Designed for good dimensional stability and low warpage, this resin also uses non-chlorinated, non-brominated FR additives to achieve a V0 UL94 rating at 1.0 mm. Noryl V02570 is may be an excellent material candidate for application requiring electrically insulating properties, low warpage and thin wall flame resistance.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, yld, Type I, 5 mm/min	75	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	75	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	3600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	120	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3800	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	73	MPa	ISO 527
Tensile Stress, break, 5 mm/min	73	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	4700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	123	MPa	ISO 178
Flexural Stress, break, 2 mm/min	115	MPa	ISO 178
Flexural Modulus, 2 mm/min	3800	MPa	ISO 178
Hardness, H358/30	115	MPa	ISO 2039-1
IMPACT	Value	Unit	Standard
Izod Impact, notched, 23°C	35	J/m	ASTM D 256
Izod Impact, notched, -30°C	35	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	9	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	25	kJ/m ²	ISO 180/1U
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m ²	ISO 179/1eU
THERMAL	Value	Unit	Standard
Vicat Softening Temp, Rate B/50	165	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	148	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.E-05	1/°C	ASTM E 831
Thermal Conductivity	0.28	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	5.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	155	°C	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	160	°C	ISO 306
Vicat Softening Temp, Rate B/120	167	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	155	°C	ISO 75/Be

HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	145	°C	ISO 75/Ae
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL	Value	Unit	Standard
Specific Gravity	1.35	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow (2)	0.3 - 0.5	%	SABIC Method
Mold Shrinkage, flow, 3.2 mm	0.3 - 0.5	%	SABIC Method
Melt Flow Rate, 300°C/5.0 kgf	12	g/10 min	ASTM D 1238
Density	1.35	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.25	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 300°C/5.0 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL	Value	Unit	Standard
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Voltage Arc Resistance {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	33	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	3	-	IEC 60250
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.005	-	IEC 60250
Dissipation Factor, 1 MHz	0.004	-	IEC 60250
Comparative Tracking Index	250	V	IEC 60112
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Recognized, 94V-0 Flame Class Rating (3)	1	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	775	°C	IEC 60695-2-13
Oxygen Index (LOI)	32	%	ISO 4589

Source GMD, last updated:01/19/2007

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	110 - 120	°C
Drying Time	2 - 4	hrs
Melt Temperature	290 - 330	°C
Nozzle Temperature	290 - 310	°C
Front - Zone 3 Temperature	310 - 330	°C
Middle - Zone 2 Temperature	290 - 310	°C
Rear - Zone 1 Temperature	270 - 290	°C
Hopper Temperature	60 - 80	°C
Mold Temperature	80 - 120	°C

Source GMD, last updated:01/19/2007

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Noryl is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company. All rights reserved